

VT-901

DATASHEET VT-901 LAMINATE / PREPREG

UL Approval: E214381 Version: B6 19/09/2016 Slash Sheets: 40/41

GENERAL INFORMATION

- Tg 250°C
- High Td
- Improved Fracture Toughness
- Low Z-axis CTE
- Meets NASA requirements for no visible bromine

APPLICATION

- Chip Manufacturers
- Engine/Flight Controls
- Power Supply /Backplane
- Military and Burn-in Board

AVAILABILITY

- Core Thickness: .002"(0.05mm) to .125"(3mm), available in sheet or panel form
- Copper Foil: 1/4oz to 6oz
- Prepregs are available in roll or panel form
- E-Glass styles: 7628, 1506, 2113, 2313, 3313, 2116, 1080, 106 etc

Note: Double side treated copper foil and reverse copper foil are not suggested using on VT-901 laminates because the peel strength would not be as good as conventional materials.

Ventec Electronics (Suzhou) Co., Ltd

168 Xiang Yang Rd
Suzhou New District
Jiangsu
P.R. China 215009

T: +86 512 6809 1810
F: +86 512 6808 1823
Email: sales@ventec.com.cn
www.ventecclaminates.com



Properties		Prepreg		Laminate
Storage Condition	Temperature	Below 23°C (73°F)	Below 5°C (41°F)	Room
	Relative humidity	Below 55% RH	/	/
Shelf Life		3 months	6 months	24 months (airproof)

The prepreg exceeding shelf life should be retested.

PROPERTIES SHEET IPC-4101D-WAM1 SPECIFICATION SHEET(S) /40/41

Properties		Test Method	Units	Specification	Typical Value
Thermal Properties					
Tg	DSC	IPC-TM-650 2.4.25	°C	-	-
	TMA	IPC-TM-650 2.4.24	°C	200 minimum	250
Td		ASTM D3850	°C	-	395
T260		IPC-TM-650 2.4.24.1	Minute	-	>60
T288		IPC-TM-650 2.4.24.1	Minute	-	>60
Thermal Stress @ 288°C		IPC-TM-650 2.4.13.1	Second	Pass 10s	>1200
Z-axis CTE	Before Tg	IPC-TM-650 2.4.24	ppm/°C	-	50
	After Tg	IPC-TM-650 2.4.24	ppm/°C	-	150
	Total Expansion (50~260°C)	IPC-TM-650 2.4.24	%	-	1.4
MOT		UL 94	°C	-	140
Electrical Properties					
DK @ 1GHz RC 40%		IPC-TM-650 2.5.5.9	-	5.4 maximum	4.05
DF @ 1GHz RC 40%		IPC-TM-650 2.5.5.9	-	0.035 maximum	0.012



Properties		Test Method	Units	Specification	Typical Value
Volume Resistivity	After Moisture Resistance	IPC-TM-650 2.4.17.1	MΩ-cm	1.0E+6 minimum	5.0E+8
	E-24/125	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+6 minimum	5.0E+6
Surface Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ	1.0E+6 minimum	5.0E+7
	E-24/125	IPC-TM-650 2.5.17.1	MΩ	1.0E+6 minimum	5.0E+6
Electrical Strength		IPC-TM-650 2.5.6.2	Volt/mil (KV/mm)	762 (30) minimum	1200~1400 (54)
Dielectric Breakdown		IPC-TM-650 2.5.6	KV	40 minimum	60
Comparative Tracking Index (CTI)		ASTM D3638	Rating (Volt)	-	Grade 4 (100~175)
Arc Resistance		ASTM D495	Second	120 minimum	150
Mechanical Properties					
Peel Strength (1oz)	As received	IPC-TM-650 2.4.8	lb/in (N/mm)	-	6~9 (1.05~1.58)
	After thermal stress	IPC-TM-650 2.4.8	lb/in (N/mm)	5.14 (0.90) minimum	6~9 (1.05~1.58)
Flexural Strength	Warp	IPC-TM-650 2.4.4	Kpsi (MPa)	60 (415) minimum	600 (87)
	Fill	IPC-TM-650 2.4.4	Kpsi (MPa)	47 (325) minimum	500 (72)
Physical Properties					
Moisture Absorption		IPC-TM-650 2.6.2.1	%	1.0 maximum	0.2
Flammability		UL-94	Rating	HB minimum	V0

Note: All test data provided are typical values and are not intended to be specification values.

Published on: 19/09/2016

22/02/2017 16:26:33 UTC